



SUBMITTAL FORM
All GreenFiber Products

Date: _____

Submitted to: _____

Submitted by: _____

Job Reference: _____

Job Name: _____

GreenFiber Corporate Office
2500 Distribution Street, Suite 200
Charlotte, NC 28203
800.228.0024 / www.greenfiber.com

UNITED STATES

Product Type	Product Code	Description	Minimum Thickness (inches)		R-value	Applicable Standards / Specifications
			Installed	Settled		
GreenFiber Stabilized Insulation	INS500 (For Attics Only) INS502	Designed for spray applied attic, wall and floor applications. Made of 85% recycled paper fibers. Remaining 15% contains dry adhesive and fire resistance additives.	3.62	3.51	R-13	Federal Regulation 16 CFR 1209, 16 CFR 1404, 16 CFR 460. ASTM C-739, ASTM E-84, Flame Spread Index <25, Smoke Developed Index <50. ICC-ES ESR-1996 Report
			5.29	5.14	R-19	
			8.36	8.11	R-30	
			10.59	10.27	R-38	
			13.65	13.24	R-49	
GreenFiber Stabilized Floor Insulation	INS730	Designed for spray applied floor applications. Made of 85% recycled paper fibers. Remaining 15% contains dry adhesive and fire resistance additives.	3.62	3.51	R-13	Federal Regulation 16 CFR 1209, 16 CFR 1404, 16 CFR 460. ASTM C-739, ASTM E-84, Flame Spread Index <25, Smoke Developed Index <50. ICC-ES ESR-1996 Report
			5.29	5.14	R-19	
			11.15	10.81	R-40	
GreenFiber All Borate Stabilized Insulation	INS735	Designed for spray applied wall applications. Can also be used in attic, dry-dense pack and floor applications. Made of 85% recycled paper fibers. Remaining 15% contains dry adhesive and fire resistance additives.	3.6	3.5	R-13	Federal Regulation 16 CFR 1209, 16 CFR 1404, 16 CFR 460. ASTM C-739, ASTM E-84, Flame Spread Index <25, Smoke Developed Index <50. ICC-ES ESR-1996 Report
			5.3	5.1	R-19	
			10.6	10.3	R-38	
			Framing	Minimum Thickness	(Sidewalls)	
			Furring	2.0	R-7.4	
			(2x4)	3.5	R-13	
			(2x6)	5.5	R-20.4	
GreenFiber Loose-fill Insulation	INS510LD	Designed for dry, spray applied attic or dry dense pack applications. Made of 85% recycled paper fibers. Remaining 15% contains fire resistance additives.	4.1	3.7	R-13	Federal Regulation 16 CFR 1209, 16 CFR 1404, 16 CFR 460. ASTM C-739, ASTM E-84, Smoke Developed Index <450. ICC-ES ESR-1996 Report
			5.9	5.3	R-19	
			9.2	8.3	R-30	
			11.6	10.5	R-38	
			14.9	13.4	R-49	
GreenFiber All Borate Loose-fill Insulation	INS760LD	Designed for dry, spray applied attic or dry dense pack applications. Made of 85% recycled paper fibers. Remaining 15% contains fire resistance additives.	4.1	3.7	R-13	Federal Regulation 16 CFR 1209, 16 CFR 1404, 16 CFR 460. ASTM C-739, ASTM E-84, Smoke Developed Index <450. ICC-ES ESR-1996 Report
			5.9	5.3	R-19	
			9.0	8.1	R-30	
			11.2	10.1	R-38	
			14.1	12.7	R-49	

GreenFiber Blow in Natural Fiber Insulation	INS551LD INS416LD	Designed for dry, spray applied attic or dry dense pack applications. Made of 85% recycled paper fibers. Remaining 15% contains fire resistance additives.	4.1	3.7	R-13	Federal Regulation 16 CFR 1209, 16 CFR 1404, 16 CFR 460. ASTM C-739, ASTM E- 84, Smoke Developed Index <450. ICC-ES ESR-1996 Report
			5.9	5.4	R-19	
			9.3	8.4	R-30	
			11.7	10.5	R-38	
			15.0	13.5	R-49	

CANADA						
Product Type	Product Code	Description	Minimum Thickness (mm)		RSI	Applicable Standards / Specifications
			Installed	Settled		
GreenFiber Stabilized Insulation	INS500-CAN	Designed for spray applied attic applications. Made of 85% recycled paper fibers. Remaining 15% contains dry adhesive and fire resistance additives.		218	RSI 5.6	CAN/ULC-S703 CAN/ULC-S102.2
				273	RSI 7.0	
				300	RSI 7.7	
				343	RSI 8.8	
				409	RSI 10.6	
GreenFiber Loose-fill Insulation	INS510LD-CAN	Designed for dry, spray applied attic or dry dense pack applications. Made of 85% recycled paper fibers. Remaining 15% contains dry adhesive and fire resistance additives.	250	225	RSI 5.6	CAN/ULC-S703 CAN/ULC-S102.2
			311	280	RSI 7.0	
			386	348	RSI 8.8	
			462	415	RSI 10.6	
GreenFiber Blow in Natural Fiber Insulation	INS550LD-CAN	Designed for dry, spray applied attic or dry dense pack applications. Made of 85% recycled paper fibers. Remaining 15% contains dry adhesive and fire resistance additives.	244	218	RSI 5.6	CAN/ULC-S703 CAN/ULC-S102.2
			306	273	RSI 7.0	
			336	300	RSI 7.7	
			385	343	RSI 8.8	
			458	409	RSI 10.6	

GREENFIBER PRODUCT ATTRIBUTES

Higher R-value

- GreenFiber Insulation provides a high R-value per inch. This means you can realize more insulating performance with less material which will save you money.*
- The Insulation fills tiny cavities and surrounds plumbing pipes and electrical wiring. It fills gaps where energy can escape and reduces air infiltration.
- By providing a better barrier against air infiltration, GreenFiber Insulation achieves a 26% increase in overall energy efficiency. (Study conducted by the University of Colorado at the Denver School of Architecture and Planning, 1989). That translates in cost savings on a month to month basis.**

**The R-value per inch of this insulation varies with thickness. The thicker the insulation, the lower the R-value per inch.*

***Savings vary. Find out why in the seller's fact sheet on R-values. Higher R-values mean greater insulating power.*

Environmentally Friendly

- Our natural fiber insulation consists of 85% recycled content. It is manufactured without using formaldehyde, asbestos, mineral fiber or fiber glass.
- Our production process utilizes energy on demand, using 10 times less energy than competitive insulation manufacturers.*

** This comparison is based on the R-19 R-value in a one-square-foot area and includes the production and energy used in the insulation manufacturing process.*

Better Sound Control

- Our insulation is two to three times denser than other insulation products. This density helps protect your home from fire and absorbs unwanted noise.
- Sound travels through the air, so our insulation's ability to fill gaps and voids creates a quieter home.
- In open attics, GreenFiber Insulation easily forms around irregular construction details and stays in place, fitting snugly against framing members and even moderate slopes.
- GreenFiber Insulation has been chosen as an enhanced sound control material for homes located in airport flight paths.

Added Fire Safety

- GreenFiber Insulation has earned a Class 1 or Class A fire rating as determined by ASTM E84.
- Our insulation is treated with safe fire retardants that exceed test requirements set by the Consumer Product Safety Commission (CPSC) standard 16 CFR Part 1209.
- Building assemblies resist fire longer when using GreenFiber Insulation than when using other materials. In a test conducted at the Maryland Fire and Rescue Institute, the structure with GreenFiber Insulation stood 57% longer than the structure with fiber glass insulation.

Test Requirements

- Our insulation meets all test requirements of ASTM C739 (US), CAN/ULC-S703 in Canada, and all FHA, VA, HUD and building code requirements. Test requirements include but are not limited to:
 - Corrosiveness
 - Critical Radiant Flux
 - Design Density
 - Flame Spread Permanency
 - Fungi Resistance
 - Moisture Vapor Sorption
 - Odor Emission
 - Separation of Chemicals
 - Smoldering Combustion
 - Surface Burning Characteristics
 - Thermal Resistance

US GreenFiber (USGF) does not provide architectural, inspection or engineering services and disclaims any responsibility with respect thereto. USGF does not guarantee, warrant or attempt to determine whether a building structure, design or the use of materials therein complies with any applicable codes, standards, guidelines or standards of workmanship. The user maintains the full and complete responsibility to comply with all codes, laws and regulations applicable to the safe and proper use, handling and installation of the product and should consult with an architect and/or engineer for all construction and design related questions. The information contained herein is believed to be accurate as of the time of preparation. However, USGF makes no warranty concerning the accuracy of this information. USGF will not be liable for claims relating to the use of information contained herein, regardless of whether it is claimed that the information or recommendations are inaccurate, incomplete or incorrect.