



ATTIC CARD

THIS IS GREENFIBER® STABILIZED FOR ATTICS ONLY
CELLULOSE INSULATION

Application Coverage Chart			30 lbs (13.6 kg)			INS506LD	
R-Value at 75° F Mean Temp. Valor de resistencia termica (valor R) a 75 F de temperatura media	Minimum Thickness (inches) Espesor minimo (en pulgadas)		Net Coverage (no adjustment for framing) Recubrimiento neto (Sin compensacion para el entramado)			Net Coverage (adjusted for 2' x 6" framing on 16" centers) Cobertura neta (con compensación para una estructura de 2' x 6" en centros de 16")	
	Initial Installed Thickness Espesor inicial instalado	Settled Thickness Espesor asentado	Maximum Sq. Ft. per Bag Metros Cuadrado máximos por bolsa	Minimum Bags per 1,000 Sq. Ft. Cantidad minima de bolsas por 1,000 pies cuadrados	Minimum Weight per Sq. Ft. (lbs/ft ²) Peso minimo por pie cuadrado (lb/pie ²)	Maximum Sq. Ft. per Bag Metros Cuadrado máximos por bolsa	Minimum Bags per 1,000 Sq. Ft. Cantidad minima de bolsas por 1,000 pies cuadrados
11	3.3	3.0	94.3	10.6	0.32	104.0	9.6
13	3.9	3.6	79.0	12.7	0.38	87.1	11.5
19	5.7	5.3	53.1	18.8	0.57	58.5	17.1
22	6.6	6.1	45.6	21.9	0.66	49.5	20.2
28	8.4	7.8	33.7	29.7	0.89	37.1	27.0
30	8.9	8.3	31.1	32.2	0.97	32.9	30.4
32	9.5	8.8	28.6	35.0	1.05	30.2	33.1
38	11.2	10.4	22.8	43.9	1.32	23.9	41.8
40	11.8	10.9	21.3	47.1	1.41	22.3	44.9
44	12.9	12.0	18.9	52.9	1.59	19.7	50.6
48	14.0	13.0	17.0	59.0	1.77	17.5	57.1
49	14.3	13.3	16.5	60.5	1.81	17.1	58.5
50	14.6	13.5	16.2	61.9	1.86	16.8	59.5
60	17.3	16.1	13.0	77.1	2.31	13.4	74.8

THE ABOVE COVERAGE CHART IS BASED ON A NOMINAL BAG WEIGHT OF 30 LBS USING A VOLUMATIC III, 3rd GEAR AND 8" GATE. THE CHART IS BASED ON SETTLED THICKNESS AND IS FOR ESTIMATING PURPOSES ONLY. JOB CONDITIONS, APPLICATION TECHNIQUES, EQUIPMENT, AND SETTINGS CAN INFLUENCE ACTUAL COVERAGE. ACTUAL COVERAGE MAY VARY BASED ON CONDITIONS AND IS NOT GUARANTEED BY THE MANUFACTURER. DO NOT EXCEED MAXIMUM SQUARE FEET COVERAGE PER BAG. THE APPLICATOR MUST INSTALL BOTH THE MINIMUM NUMBER OF BAGS PER 1000 SQ. FT. AND THE MINIMUM INSTALLED THICKNESS TO INSURE THE STATED R-VALUE HAS BEEN REACHED. FAILURE TO MEET BOTH THESE REQUIREMENTS MAY PREVENT THE ACHIEVEMENT OF THE SPECIFIED R-VALUE. THE INSTALLED MOISTURE CONTENT MUST BE BETWEEN 16% AND 25%, IN ATTIC APPLICATIONS. THIS COVERAGE CHART DOES NOT APPLY TO DRY LOOSE-FILL ATTIC/FLOOR APPLICATIONS. MINIMUM NET WEIGHT IS 28.5 LBS.

Greenfiber provides outstanding thermal performance, fire-resistance and sound control. Consisting of up to 85% recycled content, Greenfiber Insulation is specially treated for flame resistance.

R-value means resistance to heat flow - the higher the R-value, the greater the insulation power.

CERTIFICATION:

This insulation has been installed in conformance with the above recommendations, to provide a value of R-_____ using _____ bags of this insulation to cover _____ square feet of area.

Builder's Signature: _____
Company Name: _____
Date: _____

Applicator's Signature: _____
Company Name: _____
Date: _____

FOR MORE INFORMATION CONTACT GREENFIBER:

800.228.0024
greenfiber.info@greenfiber.com

Greenfiber Corporate Office
5500 77 Center Drive, Suite 100
Charlotte NC 28217
(p) 800.228.0024 (f) 704.522.3748
www.greenfiber.com

MANUFACTURING LOCATIONS:

Debert, Nova Scotia
Norfolk, NE 68701
Mesa, AZ 85212
Salt Lake City, UT 84119
Tampa, FL 33605
Waco, TX 76704
Wilkes-Barre, PA 18702

